

University of Groningen

## Catalytic molecular motors

Vicario, J; Eelkema, R; Browne, WR; Meetsma, A; Crois, René M. La; Feringa, Bernard

*Published in:*  
Chemical Communications

*DOI:*  
[10.1039/b505092h](https://doi.org/10.1039/b505092h)

**IMPORTANT NOTE:** You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

*Document Version*  
Publisher's PDF, also known as Version of record

*Publication date:*  
2005

[Link to publication in University of Groningen/UMCG research database](#)

*Citation for published version (APA):*

Vicario, J., Eelkema, R., Browne, WR., Meetsma, A., Crois, R. M. L., & Feringa, B. (2005). Catalytic molecular motors: fuelling autonomous movement by a surface bound synthetic manganese catalase. *Chemical Communications*, 34(31), 3936-3938. <https://doi.org/10.1039/b505092h>

### Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

### Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

*Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.*

```
#####  
#  
#           Cambridge Crystallographic Data Centre  
#           CCDC  
#  
#####  
#  
# This CIF contains data from an original supplementary publication  
# deposited with the CCDC, and may include chemical, crystal,  
# experimental, refinement, atomic coordinates,  
# anisotropic displacement parameters and molecular geometry data,  
# as required by the journal to which it was submitted.  
#  
# This CIF is provided on the understanding that it is used for bona  
# fide research purposes only. It may contain copyright material  
# of the CCDC or of third parties, and may not be copied or further  
# disseminated in any form, whether machine-readable or not,  
# except for the purpose of generating routine backup copies  
# on your local computer system.  
#  
# For further information on the CCDC, data deposition and  
# data retrieval see:  
#           www.ccdc.cam.ac.uk  
#  
# Bona fide researchers may freely download Mercury and enCIFer  
# from this site to visualise CIF-encoded structures and  
# to carry out CIF format checking respectively.  
#  
#####
```

data\_c22.50h2  
\_database\_code\_depnum\_ccdc\_archive 'CCDC 268595'

#=====

## # 5. CHEMICAL DATA

\_chemical\_name\_systematic

;

?

;

\_chemical\_name\_common ?

\_chemical\_melting\_point ?

\_chemical\_formula\_moiety 'C45 H41 Mn2 N6 O4, Cl O4'

\_chemical\_formula\_structural ?

# Ex: 'C12 H16 N2 O6, H2 O' and '(Cd 2+)3, (C6 N6 Cr 3-)2, 2(H2 O)'

\_chemical\_formula\_sum 'C45 H41 Cl Mn2 N6 O8'

\_chemical\_formula\_weight 939.18

\_chemical\_compound\_source 'by syntheses'

loop\_

\_atom\_type\_symbol

\_atom\_type\_description

\_atom\_type\_scatter\_dispersion\_real

\_atom\_type\_scatter\_dispersion\_imag

\_atom\_type\_scatter\_source

O O .0106 .0060 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

N N .0061 .0033 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

Mn Mn .3368 .7283 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

Cl Cl .1484 .1585 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

H H .0000 .0000 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

#=====

## # 6. CRYSTAL DATA

\_symmetry\_cell\_setting Monoclinic  
 \_symmetry\_space\_group\_name\_Hall 'C 2y'  
 \_symmetry\_space\_group\_name\_H-M 'C 2'

loop\_  
 \_symmetry\_equiv\_pos\_as\_xyz  
 x,y,z  
 -x,y,-z  
 1/2+x,1/2+y,z  
 1/2-x,1/2+y,-z

\_cell\_length\_a 15.226(2)  
 \_cell\_length\_b 12.924(2)  
 \_cell\_length\_c 10.944(2)  
 \_cell\_angle\_alpha 90  
 \_cell\_angle\_beta 90.157(9)  
 \_cell\_angle\_gamma 90  
 \_cell\_volume 2153.6(6)  
 \_cell\_formula\_units\_Z 2  
 \_cell\_measurement\_temperature 130  
 \_cell\_measurement\_reflns\_used 22  
 \_cell\_measurement\_theta\_min 16.65  
 \_cell\_measurement\_theta\_max 20.21  
 \_cell\_special\_details

;

Unit cell parameters (Duisenberg, 1992) and orientation matrix were determined from a least-squares treatment of SET4 (de Boer & Duisenberg, 1984) setting. Reduced cell calculations did not indicate any higher metric lattice symmetry and examination of the final atomic coordinates of the structure did not yield extra symmetry elements (Spek, 1988; Le Page 1987, 1988)

;

\_exptl\_crystal\_description 'cubic-shaped block'  
 \_exptl\_crystal\_colour 'light green transparent'  
 \_exptl\_crystal\_size\_max 0.25  
 \_exptl\_crystal\_size\_mid 0.25  
 \_exptl\_crystal\_size\_min 0.25  
 \_exptl\_crystal\_size\_rad ?  
 \_exptl\_crystal\_density\_meas ?  
 \_exptl\_crystal\_density\_diffn 1.448  
 \_exptl\_crystal\_density\_method ?  
 \_exptl\_crystal\_F\_000 968  
 \_exptl\_absorpt\_coefficient\_mu .71  
 \_exptl\_crystal\_density\_meas\_temp ?  
 \_exptl\_absorpt\_correction\_type none  
 \_exptl\_absorpt\_process\_details ?  
 \_exptl\_absorpt\_correction\_T\_min ?  
 \_exptl\_absorpt\_correction\_T\_max ?

#=====

## # 7. EXPERIMENTAL DATA

\_exptl\_special\_details  
 ;  
 ?  
 ;  
 \_diffn\_ambient\_temperature 130  
 \_diffn\_radiation\_wavelength .71073  
 \_diffn\_radiation\_type 'Mo K\alpha'

```

_diffrn_radiation_source 'fine focus sealed Philips Mo tube '
_diffrn_radiation_monochromator 'perpendicular mounted graphite'
_diffrn_radiation_detector
;
scintillation NaI crystal with photomultiplier
;
_diffrn_measurement_device_type
;
Enraf Nonius CAD-4F diffractometer
;

_diffrn_measurement_method \w/2\q

_diffrn_special_details
;
Crystal into the cold nitrogen stream of the low-temperature unit
(Bolhuis, 1971), on an Enraf-Nonius CAD-4F diffractometer.
Graphite-monochromated Mo K\alpha radiation,
\w/2\q scan, \D\w = (0.80 + 0.34 tg \q)\%.
;
_diffrn_detector_area_resol_mean ?

_diffrn_standards_number 3
_diffrn_standards_interval_count ?
_diffrn_standards_interval_time 180
_diffrn_standards_decay_% 3.1

loop_
_diffrn_standard_refl_index_h
_diffrn_standard_refl_index_k
_diffrn_standard_refl_index_l
1 -1 -3
2 2 0
4 0 1

# number of measured reflections (redundant set)
_diffrn_reflns_number 5221
_diffrn_reflns_av_R_equivalents 0.0111
_diffrn_reflns_av_sigmaI/netI 0.0159
_diffrn_reflns_limit_h_min -19
_diffrn_reflns_limit_h_max 19
_diffrn_reflns_limit_k_min -16
_diffrn_reflns_limit_k_max 16
_diffrn_reflns_limit_l_min -13
_diffrn_reflns_limit_l_max 0
_diffrn_reflns_theta_min 1.86
_diffrn_reflns_theta_max 26.99
_diffrn_reflns_reduction_process
;
Intensity data were corrected for Lorentz and polarization effects, scale
variation, but not for absorption and reduced to  $F_o^2$ 
;

# number of unique reflections
_reflns_number_total 4691
_reflns_number_gt 4481
_reflns_threshold_expression >2sigma(I)

_computing_data_collection 'CAD4-UNIX Software Version 5.1, 1994'
_computing_cell_refinement 'SET4 (de Boer & Duisenberg, 1984)'
_computing_data_reduction 'HELENA (Spek, 1993)'
_computing_structure_solution
;
DIRDIF-97 (Beurskens et al., 1997)
;

```

```

_computing_structure_refinement 'SHELXL-97 (Sheldrick, 1997)'
_computing_molecular_graphics
;
PLUTO (Meetsma, 1997)
ORTEP (Burnett et al., 1996)
PLATON (Spek, 1994, 1996)
;
_computing_publication_material 'PLATON (Spek, 1990)'

#=====

# 8. REFINEMENT DATA

_refine_special_details
;
Refinement of F2 against ALL reflections. The weighted R-factor wR and
goodness of fit S are based on F2, conventional R-factors R are based
on F, with F set to zero for negative F2. The threshold expression of
F2 > 2sigma(F2) is used only for calculating R-factors(gt) etc. and is
not relevant to the choice of reflections for refinement. R-factors based
on F2 are statistically about twice as large as those based on F, and R-
factors based on ALL data will be even larger.
;

_refine_ls_structure_factor_coef Fsqd
_refine_ls_matrix_type full
_refine_ls_weighting_scheme
'calc w=1/[s2(F2)+(0.0422P)2+2.3179P] where P=(F2+2Fc2)/3'
_atom_sites_solution_primary heavy
_atom_sites_solution_secondary difmap
_atom_sites_solution_hydrogens difmap
_refine_ls_hydrogen_treatment mixed
_refine_ls_extinction_method none
_refine_ls_extinction_coef ?
_refine_ls_abs_structure_details 'Flack H D (1983), Acta Cryst. A39, 876-881'
_refine_ls_abs_structure_Flack 0.428(15)
_refine_ls_number_reflns 4691
_refine_ls_number_parameters 375
_refine_ls_number_restraints 1
_refine_ls_R_factor_all 0.0329
_refine_ls_R_factor_gt 0.0303
_refine_ls_wR_factor_ref 0.0778
_refine_ls_wR_factor_gt 0.0760
_refine_ls_goodness_of_fit_ref 1.027
_refine_ls_restrained_S_all 1.026
_refine_ls_shift/su_max 0.001
_refine_ls_shift/su_mean 0.000

_refine_diff_density_max .551
_refine_diff_density_min -.520
_refine_diff_density_rms .051

#=====

# 9. ATOMIC COORDINATES AND THERMAL PARAMETERS

loop_
_atom_site_label
_atom_site_thermal_displace_type
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_occupancy
_atom_site_U_iso_or_equiv
Mn Uani .07875(2) .00111(2) .41011(3) 1.000 .0241(1)
O1 Uani .05356(11) -.04469(14) .59691(14) 1.000 .0301(5)

```

```

O2 Uani .04933(13) .16203(14) .42542(18) 1.000 .0368(6)
N1 Uani .22262(11) -.00802(18) .46914(15) 1.000 .0248(5)
N2 Uani .16141(14) .07360(16) .24962(17) 1.000 .0289(6)
N3 Uani .13522(15) -.14282(15) .31559(18) 1.000 .0305(6)
C1 Uani .10637(15) -.04535(18) .6956(2) 1.000 .0259(6)
C2 Uani .07153(17) -.02851(19) .8126(2) 1.000 .0311(7)
C3 Uani .12479(18) -.03113(19) .9157(2) 1.000 .0327(7)
C4 Uani .21384(18) -.04843(19) .9051(2) 1.000 .0313(7)
C5 Uani .24910(16) -.06486(18) .7896(2) 1.000 .0279(7)
C6 Uani .19682(15) -.06438(17) .68488(19) 1.000 .0248(6)
C7 Uani .23652(17) -.09017(19) .5627(2) 1.000 .0272(7)
C8 Uani .25689(18) .0923(2) .5127(2) 1.000 .0314(8)
C9 Uani .26415(17) -.03766(18) .3515(2) 1.000 .0283(7)
C10 Uani .24612(17) .04740(19) .2596(2) 1.000 .0290(7)
C11 Uani .3115(2) .0945(2) .1919(2) 1.000 .0353(8)
C12 Uani .2879(2) .1746(2) .1141(2) 1.000 .0418(9)
C13 Uani .2009(2) .2028(2) .1043(2) 1.000 .0385(8)
C14 Uani .1392(2) .15075(19) .1740(2) 1.000 .0346(8)
C15 Uani .22261(18) -.13645(18) .3031(2) 1.000 .0299(7)
C16 Uani .2720(2) -.2106(2) .2432(2) 1.000 .0394(9)
C17 Uani .2290(3) -.2947(2) .1941(2) 1.000 .0479(11)
C18 Uani .1395(3) -.3023(2) .2053(2) 1.000 .0485(12)
C19 Uani .0944(2) -.2250(2) .2670(2) 1.000 .0402(9)
C20 Uani .00000 .2060(3) .50000 1.000 .0305(10)
C21 Uani .00000 .3227(3) .50000 1.000 .0416(13)
C22 Uani .01555(18) .3763(3) .3925(4) 1.000 .0535(12)
C23 Uani .0147(2) .4842(3) .3941(6) 1.000 .0804(19)
C24 Uani .00000 .5373(4) .50000 1.000 .100(3)
C1 Uani .00000 .42958(9) .00000 1.000 .0390(3)
O3 Uani .0701(4) .3798(6) -.0492(7) 1.000 .195(3)
O42 Uani .0385(7) .4529(11) .1085(11) .605(17) .161(5)
O41 Uani .0200(11) .5295(11) .0434(11) .395(17) .115(6)
H2 Uiso .009(2) -.010(3) .821(3) 1.000 .056(9)
H3 Uiso .093(2) -.018(3) 1.000(3) 1.000 .069(11)
H4 Uiso .257(2) -.046(3) .984(3) 1.000 .046(9)
H5 Uiso .311(2) -.080(3) .782(3) 1.000 .037(8)
H7 Uiso .2993(18) -.101(2) .577(2) 1.000 .020(6)
H7' Uiso .2100(18) -.152(2) .527(3) 1.000 .024(6)
H8 Uiso .2441(19) .150(3) .458(3) 1.000 .033(7)
H8' Uiso .324(2) .089(3) .524(3) 1.000 .044(9)
H8" Uiso .228(2) .102(3) .600(3) 1.000 .045(9)
H9 Uiso .3258(19) -.047(2) .364(2) 1.000 .029(7)
H11 Uiso .374(2) .071(3) .201(3) 1.000 .047(9)
H12 Uiso .331(3) .204(3) .074(4) 1.000 .062(11)
H13 Uiso .184(2) .259(3) .055(3) 1.000 .046(9)
H14 Uiso .071(2) .172(3) .172(3) 1.000 .042(8)
H16 Uiso .330(3) -.201(4) .227(4) 1.000 .077(14)
H17 Uiso .258(3) -.348(4) .152(4) 1.000 .073(12)
H18 Uiso .108(3) -.351(4) .178(4) 1.000 .066(12)
H19 Uiso .031(2) -.227(2) .276(3) 1.000 .033(7)
H22 Uiso .029(2) .342(3) .334(3) 1.000 .049(11)
H23 Uiso .023(3) .513(4) .329(4) 1.000 .065(12)
H24 Uiso .00000 .616(7) .50000 1.000 .11(3)

loop_
_atom_site_aniso_label
_atom_site_aniso_U_11
_atom_site_aniso_U_22
_atom_site_aniso_U_33
_atom_site_aniso_U_23
_atom_site_aniso_U_13
_atom_site_aniso_U_12
Mn .0288(2) .0259(2) .0177(1) -.0006(1) -.0019(1) .0006(2)
O1 .0312(8) .0421(9) .0170(7) .0003(6) -.0034(6) .0072(7)
O2 .0407(10) .0274(9) .0424(10) .0026(8) .0084(8) .0040(7)
N1 .0321(8) .0225(9) .0197(7) -.0030(8) .0001(6) .0014(9)

```

```

N2 .0424(12) .0230(9) .0212(9) -.0008(7) .0022(8) .0002(8)
N3 .0459(12) .0250(10) .0206(9) -.0031(7) -.0011(8) -.0025(9)
C1 .0339(12) .0251(10) .0187(10) .0008(8) -.0040(9) .0043(9)
C2 .0355(12) .0388(14) .0189(10) -.0001(9) -.0003(9) .0055(9)
C3 .0478(14) .0324(12) .0179(10) -.0023(8) -.0023(9) .0023(10)
C4 .0459(14) .0264(12) .0216(11) .0022(9) -.0108(10) -.0019(10)
C5 .0343(12) .0254(11) .0241(11) .0051(9) -.0040(9) .0012(9)
C6 .0324(11) .0221(10) .0198(10) .0006(8) -.0041(8) .0035(9)
C7 .0317(12) .0275(12) .0225(12) .0006(9) -.0013(9) .0070(9)
C8 .0373(14) .0289(13) .0281(13) -.0059(10) -.0029(10) -.0019(10)
C9 .0332(12) .0253(10) .0263(12) -.0026(9) .0024(9) .0011(9)
C10 .0434(14) .0251(11) .0185(10) -.0051(9) .0002(9) -.0024(10)
C11 .0450(15) .0388(14) .0222(11) -.0040(10) .0068(10) -.0068(11)
C12 .0619(18) .0391(15) .0243(12) .0007(11) .0082(12) -.0155(13)
C13 .0663(19) .0265(12) .0228(11) .0016(10) -.0011(12) -.0052(12)
C14 .0583(17) .0259(11) .0197(11) -.0025(9) -.0022(10) .0012(11)
C15 .0478(14) .0248(11) .0170(10) .0008(8) .0033(9) .0043(10)
C16 .0666(19) .0269(13) .0248(12) .0046(9) .0117(12) .0100(12)
C17 .097(3) .0239(12) .0229(12) .0010(10) .0154(14) .0052(14)
C18 .100(3) .0222(12) .0232(13) -.0031(10) -.0009(14) -.0128(14)
C19 .067(2) .0298(13) .0237(12) .0012(10) -.0031(12) -.0129(13)
C20 .0212(15) .0259(16) .0444(19) .0000 -.0022(13) .0000
C21 .0155(15) .0252(17) .084(3) .0000 .0082(17) .0000
C22 .0198(12) .0357(15) .105(3) .0176(18) .0148(15) .0023(11)
C23 .0304(14) .036(2) .175(5) .038(2) .037(2) .0064(13)
C24 .030(2) .025(2) .246(10) .0000 .053(4) .0000
C1 .0301(4) .0532(6) .0337(5) .0000 .0001(3) .0000
O3 .138(4) .220(7) .226(6) .006(5) .028(4) .131(5)
O42 .166(7) .158(11) .158(8) -.039(8) -.127(7) .012(7)
O41 .157(14) .104(9) .084(8) -.049(6) .024(7) -.098(10)

```

#=====

# # 10. MOLECULAR GEOMETRY

\_geom\_special\_details

;

Bond distances, angles etc. have been calculated using the rounded fractional coordinates. All esds are estimated from the variances of the (full) variance-covariance matrix. The cell esds are taken into account in the estimation of distances, angles and torsion angles

;

loop\_

\_geom\_bond\_atom\_site\_label\_1

\_geom\_bond\_atom\_site\_label\_2

\_geom\_bond\_distance

\_geom\_bond\_site\_symmetry\_1

\_geom\_bond\_site\_symmetry\_2

\_geom\_bond\_publ\_flag

Mn O1 2.1636(16) . . yes

Mn O2 2.1341(19) . . yes

Mn N1 2.2852(17) . . yes

Mn N2 2.358(2) . . yes

Mn N3 2.297(2) . . yes

Mn O1 2.1009(18) . 2\_556 yes

C1 O41 1.409(14) . . yes

C1 O3 1.359(7) . . yes

C1 O42 1.357(12) . . yes

O1 C1 1.345(3) . . yes

O2 C20 1.248(3) . . yes

O41 O41 1.127(19) . 2\_555 yes

N1 C8 1.476(3) . . yes

N1 C9 1.486(3) . . yes

N1 C7 1.490(3) . . yes

N2 C10 1.338(3) . . yes  
 N2 C14 1.339(3) . . yes  
 N3 C19 1.340(3) . . yes  
 N3 C15 1.341(4) . . yes  
 C1 C6 1.404(3) . . no  
 C1 C2 1.404(3) . . no  
 C2 C3 1.388(3) . . no  
 C3 C4 1.379(4) . . no  
 C4 C5 1.391(3) . . no  
 C5 C6 1.394(3) . . no  
 C6 C7 1.506(3) . . no  
 C9 C15 1.520(3) . . no  
 C9 C10 1.515(3) . . no  
 C10 C11 1.384(4) . . no  
 C11 C12 1.387(4) . . no  
 C12 C13 1.378(4) . . no  
 C13 C14 1.386(4) . . no  
 C15 C16 1.384(4) . . no  
 C16 C17 1.377(4) . . no  
 C17 C18 1.372(6) . . no  
 C18 C19 1.389(4) . . no  
 C20 C21 1.508(5) . . no  
 C21 C22 1.386(5) . . no  
 C22 C23 1.395(5) . . no  
 C23 C24 1.366(6) . . no  
 C2 H2 .99(3) . . no  
 C3 H3 1.06(3) . . no  
 C4 H4 1.08(3) . . no  
 C5 H5 .97(3) . . no  
 C7 H7 .98(3) . . no  
 C7 H7' .98(3) . . no  
 C8 H8" 1.06(3) . . no  
 C8 H8 .98(4) . . no  
 C8 H8' 1.03(3) . . no  
 C9 H9 .96(3) . . no  
 C11 H11 1.00(3) . . no  
 C12 H12 .88(4) . . no  
 C13 H13 .94(4) . . no  
 C14 H14 1.07(3) . . no  
 C16 H16 .91(5) . . no  
 C17 H17 .94(5) . . no  
 C18 H18 .85(5) . . no  
 C19 H19 .97(3) . . no  
 C22 H22 .81(3) . . no  
 C23 H23 .81(5) . . no  
 C24 H24 1.02(9) . . no

loop\_  
 \_geom\_angle\_atom\_site\_label\_1  
 \_geom\_angle\_atom\_site\_label\_2  
 \_geom\_angle\_atom\_site\_label\_3  
 \_geom\_angle  
 \_geom\_angle\_site\_symmetry\_1  
 \_geom\_angle\_site\_symmetry\_2  
 \_geom\_angle\_site\_symmetry\_3  
 \_geom\_angle\_publ\_flag  
 O1 Mn O2 98.90(7) . . . yes  
 O1 Mn N1 83.74(6) . . . yes  
 O1 Mn N2 155.37(7) . . . yes  
 O1 Mn N3 105.76(7) . . . yes  
 O1 Mn O1 77.59(6) . . 2\_556 yes  
 O2 Mn N1 103.26(8) . . . yes  
 O2 Mn N2 77.52(7) . . . yes  
 O2 Mn N3 154.64(7) . . . yes  
 O1 Mn O2 94.36(7) 2\_556 . . yes  
 N1 Mn N2 73.61(7) . . . yes



N1 Mn N3 74.08(8) . . . yes  
 O1 Mn N1 156.08(7) 2\_556 . . yes  
 N2 Mn N3 77.59(7) . . . yes  
 O1 Mn N2 126.76(7) 2\_556 . . yes  
 O1 Mn N3 96.63(7) 2\_556 . . yes  
 O3 C1 O41 118.0(7) . . 2\_555 yes  
 O3 C1 O42 95.5(6) 2\_555 . . yes  
 O42 C1 O42 154.3(9) . . 2\_555 yes  
 O3 C1 O42 96.5(6) . . . yes  
 O3 C1 O41 113.5(7) . . . yes  
 O3 C1 O3 123.5(5) . . 2\_555 yes  
 O3 C1 O42 95.5(6) . . 2\_555 yes  
 O3 C1 O41 118.0(7) 2\_555 . . yes  
 O41 C1 O41 47.1(8) . . 2\_555 yes  
 O3 C1 O42 96.5(6) 2\_555 . 2\_555 yes  
 O3 C1 O41 113.5(7) 2\_555 . 2\_555 yes  
 Mn O1 Mn 93.49(7) . . 2\_556 yes  
 Mn O1 C1 127.04(14) 2\_556 . . yes  
 Mn O1 C1 130.80(14) . . . yes  
 Mn O2 C20 128.5(2) . . . yes  
 C1 O41 O41 66.4(10) . . 2\_555 yes  
 Mn N1 C9 100.27(13) . . . yes  
 C7 N1 C9 110.59(19) . . . yes  
 C8 N1 C9 110.81(18) . . . yes  
 C7 N1 C8 110.77(17) . . . yes  
 Mn N1 C7 111.43(14) . . . yes  
 Mn N1 C8 112.56(15) . . . yes  
 C10 N2 C14 118.7(2) . . . yes  
 Mn N2 C10 110.80(15) . . . yes  
 Mn N2 C14 128.47(18) . . . yes  
 C15 N3 C19 117.9(2) . . . yes  
 Mn N3 C19 130.31(19) . . . yes  
 Mn N3 C15 111.66(15) . . . yes  
 O1 C1 C6 121.23(19) . . . yes  
 C2 C1 C6 118.4(2) . . . no  
 O1 C1 C2 120.3(2) . . . yes  
 C1 C2 C3 121.1(2) . . . no  
 C2 C3 C4 120.5(2) . . . no  
 C3 C4 C5 118.9(2) . . . no  
 C4 C5 C6 121.7(2) . . . no  
 C1 C6 C7 120.6(2) . . . no  
 C5 C6 C7 120.0(2) . . . no  
 C1 C6 C5 119.4(2) . . . no  
 N1 C7 C6 113.32(19) . . . yes  
 N1 C9 C10 108.14(19) . . . yes  
 N1 C9 C15 109.9(2) . . . yes  
 C10 C9 C15 107.69(19) . . . no  
 C9 C10 C11 123.1(2) . . . no  
 N2 C10 C11 122.7(2) . . . yes  
 N2 C10 C9 114.3(2) . . . yes  
 C10 C11 C12 118.1(3) . . . no  
 C11 C12 C13 119.5(3) . . . no  
 C12 C13 C14 118.8(2) . . . no  
 N2 C14 C13 122.1(3) . . . yes  
 N3 C15 C9 115.4(2) . . . yes  
 N3 C15 C16 123.1(2) . . . yes  
 C9 C15 C16 121.4(2) . . . no  
 C15 C16 C17 118.2(3) . . . no  
 C16 C17 C18 119.5(3) . . . no  
 C17 C18 C19 119.0(3) . . . no  
 N3 C19 C18 122.3(3) . . . yes  
 O2 C20 O2 125.8(3) . . 2\_556 yes  
 O2 C20 C21 117.10(18) 2\_556 . . yes  
 O2 C20 C21 117.10(18) . . . yes  
 C22 C21 C22 120.0(4) . . 2\_556 no  
 C20 C21 C22 120.0(2) . . 2\_556 no

C20 C21 C22 120.0(2) . . . no  
 C21 C22 C23 119.2(4) . . . no  
 C22 C23 C24 121.0(5) . . . no  
 C23 C24 C23 119.7(5) . . 2\_556 no  
 C1 C2 H2 119.3(19) . . . no  
 C3 C2 H2 119.5(19) . . . no  
 C4 C3 H3 123.5(17) . . . no  
 C2 C3 H3 116.0(17) . . . no  
 C3 C4 H4 121.5(17) . . . no  
 C5 C4 H4 119.6(17) . . . no  
 C4 C5 H5 119(2) . . . no  
 C6 C5 H5 119(2) . . . no  
 C6 C7 H7 106.5(13) . . . no  
 C6 C7 H7' 111.7(18) . . . no  
 H7 C7 H7' 110(2) . . . no  
 N1 C7 H7 110.4(14) . . . no  
 N1 C7 H7' 104.5(18) . . . no  
 H8 C8 H8' 108(3) . . . no  
 H8 C8 H8" 112(3) . . . no  
 H8' C8 H8" 108(2) . . . no  
 N1 C8 H8" 104(2) . . . no  
 N1 C8 H8 114(2) . . . no  
 N1 C8 H8' 111(2) . . . no  
 N1 C9 H9 109.2(13) . . . no  
 C10 C9 H9 111.3(15) . . . no  
 C15 C9 H9 110.6(15) . . . no  
 C12 C11 H11 122(2) . . . no  
 C10 C11 H11 120(2) . . . no  
 C11 C12 H12 116(3) . . . no  
 C13 C12 H12 125(3) . . . no  
 C14 C13 H13 120.4(19) . . . no  
 C12 C13 H13 120.7(19) . . . no  
 N2 C14 H14 116.5(19) . . . no  
 C13 C14 H14 121.4(19) . . . no  
 C15 C16 H16 122(3) . . . no  
 C17 C16 H16 119(3) . . . no  
 C18 C17 H17 117(3) . . . no  
 C16 C17 H17 123(3) . . . no  
 C17 C18 H18 126(3) . . . no  
 C19 C18 H18 115(3) . . . no  
 N3 C19 H19 116.2(17) . . . no  
 C18 C19 H19 121.6(17) . . . no  
 C21 C22 H22 116(3) . . . no  
 C23 C22 H22 124(3) . . . no  
 C22 C23 H23 116(4) . . . no  
 C24 C23 H23 123(4) . . . no  
 C23 C24 H24 120.2(3) 2\_556 . . no  
 C23 C24 H24 120.2(3) . . . no

loop\_

\_geom\_torsion\_atom\_site\_label\_1  
 \_geom\_torsion\_atom\_site\_label\_2  
 \_geom\_torsion\_atom\_site\_label\_3  
 \_geom\_torsion\_atom\_site\_label\_4  
 \_geom\_torsion  
 \_geom\_torsion\_site\_symmetry\_1  
 \_geom\_torsion\_site\_symmetry\_2  
 \_geom\_torsion\_site\_symmetry\_3  
 \_geom\_torsion\_site\_symmetry\_4  
 \_geom\_torsion\_publ\_flag  
 O2 Mn O1 C1 -87.5(2) . . . . no  
 O2 Mn O1 Mn 60.70(8) . . . 2\_556 no  
 N1 Mn O1 C1 15.0(2) . . . . no  
 N1 Mn O1 Mn 163.20(8) . . . 2\_556 no  
 N2 Mn O1 C1 -8.1(3) . . . . no  
 N2 Mn O1 Mn 140.13(14) . . . 2\_556 no

N3 Mn O1 C1 86.5(2) . . . . no  
 N3 Mn O1 Mn -125.32(8) . . . 2\_556 no  
 O1 Mn O1 C1 180.0(2) 2\_556 . . . no  
 O1 Mn O1 Mn -31.84(7) 2\_556 . . 2\_556 no  
 O1 Mn O2 C20 -25.47(17) . . . . no  
 N1 Mn O2 C20 -111.09(16) . . . . no  
 N2 Mn O2 C20 179.34(18) . . . . no  
 N3 Mn O2 C20 168.16(15) . . . . no  
 O1 Mn O2 C20 52.62(17) 2\_556 . . . no  
 O1 Mn N1 C7 32.62(14) . . . . no  
 O1 Mn N1 C8 -92.52(14) . . . . no  
 O1 Mn N1 C9 149.69(15) . . . . no  
 O2 Mn N1 C7 130.32(15) . . . . no  
 O2 Mn N1 C8 5.18(15) . . . . no  
 O2 Mn N1 C9 -112.61(14) . . . . no  
 N2 Mn N1 C7 -157.19(16) . . . . no  
 N2 Mn N1 C8 77.67(14) . . . . no  
 N2 Mn N1 C9 -40.12(14) . . . . no  
 N3 Mn N1 C7 -75.77(15) . . . . no  
 N3 Mn N1 C8 159.10(15) . . . . no  
 N3 Mn N1 C9 41.31(14) . . . . no  
 O1 Mn N1 C7 -6.1(3) 2\_556 . . . no  
 O1 Mn N1 C8 -131.20(18) 2\_556 . . . no  
 O1 Mn N1 C9 111.01(18) 2\_556 . . . no  
 O1 Mn N2 C10 40.6(3) . . . . no  
 O1 Mn N2 C14 -122.9(2) . . . . no  
 O2 Mn N2 C10 124.70(17) . . . . no  
 O2 Mn N2 C14 -38.8(2) . . . . no  
 N1 Mn N2 C10 16.64(16) . . . . no  
 N1 Mn N2 C14 -146.9(2) . . . . no  
 N3 Mn N2 C10 -60.18(16) . . . . no  
 N3 Mn N2 C14 136.3(2) . . . . no  
 O1 Mn N2 C10 -149.21(15) 2\_556 . . . no  
 O1 Mn N2 C14 47.3(2) 2\_556 . . . no  
 O1 Mn N3 C15 -102.36(16) . . . . no  
 O1 Mn N3 C19 82.1(2) . . . . no  
 O2 Mn N3 C15 63.6(3) . . . . no  
 O2 Mn N3 C19 -111.9(2) . . . . no  
 N1 Mn N3 C15 -23.79(15) . . . . no  
 N1 Mn N3 C19 160.7(2) . . . . no  
 N2 Mn N3 C15 52.46(15) . . . . no  
 N2 Mn N3 C19 -123.1(2) . . . . no  
 O1 Mn N3 C15 178.71(15) 2\_556 . . . no  
 O1 Mn N3 C19 3.2(2) 2\_556 . . . no  
 O1 Mn O1 Mn 30.81(6) . . 2\_556 2\_556 no  
 O1 Mn O1 C1 -179.2(2) . . 2\_556 2\_556 no  
 O2 Mn O1 Mn -67.35(8) . . 2\_556 2\_556 no  
 O2 Mn O1 C1 82.66(19) . . 2\_556 2\_556 no  
 N1 Mn O1 Mn 70.31(18) . . 2\_556 2\_556 no  
 N1 Mn O1 C1 -139.67(19) . . 2\_556 2\_556 no  
 N2 Mn O1 Mn -145.02(7) . . 2\_556 2\_556 no  
 N2 Mn O1 C1 5.0(2) . . 2\_556 2\_556 no  
 N3 Mn O1 Mn 135.55(7) . . 2\_556 2\_556 no  
 N3 Mn O1 C1 -74.44(19) . . 2\_556 2\_556 no  
 Mn O1 C1 C2 148.59(18) . . . . no  
 Mn O1 C1 C6 -32.4(3) . . . . no  
 Mn O1 C1 C2 9.8(3) 2\_556 . . . no  
 Mn O1 C1 C6 -171.22(16) 2\_556 . . . no  
 Mn O2 C20 C21 172.58(10) . . . . no  
 Mn O2 C20 O2 -7.4(2) . . . 2\_556 no  
 Mn N1 C7 C6 -70.0(2) . . . . no  
 C8 N1 C7 C6 56.1(3) . . . . no  
 C9 N1 C7 C6 179.3(2) . . . . no  
 Mn N1 C9 C10 61.1(2) . . . . no  
 Mn N1 C9 C15 -56.3(2) . . . . no  
 C7 N1 C9 C10 178.75(19) . . . . no

C7 N1 C9 C15 61.4(2) . . . . no  
 C8 N1 C9 C10 -58.0(2) . . . . no  
 C8 N1 C9 C15 -175.34(19) . . . . no  
 Mn N2 C10 C9 12.2(2) . . . . no  
 Mn N2 C10 C11 -167.52(19) . . . . no  
 C14 N2 C10 C9 177.6(2) . . . . no  
 C14 N2 C10 C11 -2.2(3) . . . . no  
 Mn N2 C14 C13 163.62(17) . . . . no  
 C10 N2 C14 C13 1.2(3) . . . . no  
 Mn N3 C15 C9 -.6(2) . . . . no  
 Mn N3 C15 C16 -176.42(18) . . . . no  
 C19 N3 C15 C9 175.5(2) . . . . no  
 C19 N3 C15 C16 -.3(3) . . . . no  
 Mn N3 C19 C18 175.36(17) . . . . no  
 C15 N3 C19 C18 .1(3) . . . . no  
 O1 C1 C2 C3 178.6(2) . . . . no  
 C6 C1 C2 C3 -.4(4) . . . . no  
 O1 C1 C6 C5 -179.7(2) . . . . no  
 O1 C1 C6 C7 -3.2(3) . . . . no  
 C2 C1 C6 C5 -.7(3) . . . . no  
 C2 C1 C6 C7 175.8(2) . . . . no  
 C1 C2 C3 C4 1.3(4) . . . . no  
 C2 C3 C4 C5 -1.0(4) . . . . no  
 C3 C4 C5 C6 -.1(4) . . . . no  
 C4 C5 C6 C1 .9(3) . . . . no  
 C4 C5 C6 C7 -175.5(2) . . . . no  
 C5 C6 C7 N1 -124.5(2) . . . . no  
 C1 C6 C7 N1 59.1(3) . . . . no  
 N1 C9 C10 C11 127.9(2) . . . . no  
 N1 C9 C10 N2 -51.9(3) . . . . no  
 N1 C9 C15 N3 40.8(3) . . . . no  
 C15 C9 C10 N2 66.9(3) . . . . no  
 C15 C9 C10 C11 -113.4(3) . . . . no  
 C10 C9 C15 C16 99.0(3) . . . . no  
 N1 C9 C15 C16 -143.4(2) . . . . no  
 C10 C9 C15 N3 -76.8(2) . . . . no  
 N2 C10 C11 C12 2.4(4) . . . . no  
 C9 C10 C11 C12 -177.3(2) . . . . no  
 C10 C11 C12 C13 -1.6(4) . . . . no  
 C11 C12 C13 C14 .7(4) . . . . no  
 C12 C13 C14 N2 -.5(4) . . . . no  
 C9 C15 C16 C17 -175.4(2) . . . . no  
 N3 C15 C16 C17 .1(3) . . . . no  
 C15 C16 C17 C18 .3(3) . . . . no  
 C16 C17 C18 C19 -.5(4) . . . . no  
 C17 C18 C19 N3 .3(4) . . . . no  
 O2 C20 C21 C22 31.18(17) . . . . no  
 O2 C20 C21 C22 -148.82(17) . . . 2\_556 no  
 O2 C20 C21 C22 -148.82(17) 2\_556 . . . no  
 C20 C21 C22 C23 179.6(2) . . . . no  
 C22 C21 C22 C23 -.4(3) 2\_556 . . . no  
 C21 C22 C23 C24 .9(4) . . . . no  
 C22 C23 C24 C23 -.4(4) . . . 2\_556 no

loop\_

\_geom\_contact\_atom\_site\_label\_1  
 \_geom\_contact\_atom\_site\_label\_2  
 \_geom\_contact\_distance  
 \_geom\_contact\_site\_symmetry\_1  
 \_geom\_contact\_site\_symmetry\_2  
 \_geom\_contact\_publ\_flag  
 Mn H2 2.86(3) . 2\_556 no  
 O3 C16 3.418(7) . 4\_555 no  
 O41 C18 3.340(15) . 1\_565 no  
 O42 C22 3.282(13) . . no  
 O42 C23 3.173(14) . . no

O1 H7' 2.86(3) . . no  
O2 H14 2.80(3) . . no  
O2 H22 2.55(4) . . no  
O3 H4 2.89(3) . 4\_556 no  
O3 H13 2.60(3) . . no  
O3 H16 2.68(5) . 4\_555 no  
O41 H11 2.87(4) . 3\_455 no  
O41 H18 2.52(5) . 1\_565 no  
O42 H5 2.62(3) . 4\_556 no  
O42 H18 2.85(5) . 1\_565 no  
O42 H22 2.86(4) . . no  
O42 H23 2.55(5) . . no  
N2 H2 2.91(3) . 2\_556 no  
N2 H8 2.78(3) . . no  
N3 H7' 2.58(3) . . no  
C1 C8 3.528(3) . . no  
C4 C17 3.563(4) . 4\_556 no  
C4 C13 3.469(4) . 4\_546 no  
C4 C12 3.586(4) . 4\_546 no  
C5 C17 3.512(4) . 4\_556 no  
C5 C12 3.573(4) . 4\_546 no  
C5 C13 3.308(4) . 4\_546 no  
C8 C17 3.531(3) . 4\_556 no  
C8 C1 3.528(3) . . no  
C12 C5 3.573(4) . 4\_556 no  
C12 C17 3.405(3) . 4\_555 no  
C12 C4 3.586(4) . 4\_556 no  
C13 C17 3.439(3) . 4\_555 no  
C13 C5 3.308(4) . 4\_556 no  
C13 C4 3.469(4) . 4\_556 no  
C16 O3 3.418(7) . 4\_545 no  
C17 C5 3.512(4) . 4\_546 no  
C17 C12 3.405(3) . 4\_545 no  
C17 C8 3.531(3) . 4\_546 no  
C17 C13 3.439(3) . 4\_545 no  
C17 C4 3.563(4) . 4\_546 no  
C18 O41 3.340(15) . 1\_545 no  
C22 O42 3.282(13) . . no  
C23 O42 3.173(14) . . no  
C1 H8" 2.86(3) . . no  
C3 H17 3.06(5) . 4\_556 no  
C4 H13 2.97(4) . 4\_546 no  
C4 H17 2.70(5) . 4\_556 no  
C5 H17 2.88(5) . 4\_556 no  
C5 H13 3.02(4) . 4\_546 no  
C5 H8" 3.01(4) . . no  
C6 H8" 2.39(4) . . no  
C10 H8 2.54(3) . . no  
C11 H4 3.03(4) . 1\_554 no  
C12 H17 3.01(4) . 4\_555 no  
C13 H17 2.95(4) . 4\_555 no  
C13 H5 3.08(4) . 4\_556 no  
C14 H2 3.07(3) . 2\_556 no  
C14 H3 2.98(4) . 1\_554 no  
C15 H7' 2.47(3) . . no  
C16 H8" 2.97(4) . 4\_546 no  
C17 H12 3.07(4) . 4\_545 no  
C17 H8" 2.70(3) . 4\_546 no  
C18 H12 3.09(4) . 4\_545 no  
C22 H7 2.85(3) . 4\_556 no  
C22 H9 3.07(3) . 3\_455 no  
C23 H8' 2.94(3) . 4\_556 no  
C23 H9 2.92(3) . 3\_455 no  
C23 H7 3.05(3) . 4\_556 no  
C24 H8' 2.77(3) . 3\_455 no  
C24 H8' 2.77(3) . 4\_556 no

H2 Mn 2.86(3) . 2\_556 no  
H2 H3 2.51(5) . 2\_557 no  
H2 N2 2.91(3) . 2\_556 no  
H2 C14 3.07(3) . 2\_556 no  
H3 H2 2.51(5) . 2\_557 no  
H3 C14 2.98(4) . 1\_556 no  
H4 O3 2.89(3) . 4\_546 no  
H4 C11 3.03(4) . 1\_556 no  
H5 C13 3.08(4) . 4\_546 no  
H5 O42 2.62(3) . 4\_546 no  
H5 H7 2.27(4) . . no  
H7 H8' 2.55(5) . . no  
H7 H9 2.47(3) . . no  
H7 H5 2.27(4) . . no  
H7 C23 3.05(3) . 4\_546 no  
H7 C22 2.85(3) . 4\_546 no  
H7' N3 2.58(3) . . no  
H7' O1 2.86(3) . . no  
H7' C15 2.47(3) . . no  
H8 N2 2.78(3) . . no  
H8 C10 2.54(3) . . no  
H8' C23 2.94(3) . 4\_546 no  
H8' C24 2.77(3) . 4\_546 no  
H8' H7 2.55(5) . . no  
H8' H9 2.48(4) . . no  
H8' C24 2.77(3) . 3\_545 no  
H8" C17 2.70(3) . 4\_556 no  
H8" C5 3.01(4) . . no  
H8" C6 2.39(4) . . no  
H8" C1 2.86(3) . . no  
H8" C16 2.97(4) . 4\_556 no  
H9 H7 2.47(3) . . no  
H9 H8' 2.48(4) . . no  
H9 H11 2.46(4) . . no  
H9 H16 2.49(5) . . no  
H9 C22 3.07(3) . 3\_545 no  
H9 C23 2.92(3) . 3\_545 no  
H11 H9 2.46(4) . . no  
H11 O41 2.87(4) . 3\_545 no  
H12 C17 3.07(4) . 4\_555 no  
H12 C18 3.09(4) . 4\_555 no  
H13 O3 2.60(3) . . no  
H13 C5 3.02(4) . 4\_556 no  
H13 C4 2.97(4) . 4\_556 no  
H14 O2 2.80(3) . . no  
H16 O3 2.68(5) . 4\_545 no  
H16 H9 2.49(5) . . no  
H17 C4 2.70(5) . 4\_546 no  
H17 C3 3.06(5) . 4\_546 no  
H17 C12 3.01(4) . 4\_545 no  
H17 C13 2.95(4) . 4\_545 no  
H17 C5 2.88(5) . 4\_546 no  
H18 O41 2.52(5) . 1\_545 no  
H18 O42 2.85(5) . 1\_545 no  
H22 O2 2.55(4) . . no  
H22 O42 2.86(4) . . no  
H23 O42 2.55(5) . . no

loop\_  
\_geom\_hbond\_atom\_site\_label\_D  
\_geom\_hbond\_atom\_site\_label\_H  
\_geom\_hbond\_atom\_site\_label\_A  
\_geom\_hbond\_distance\_DH  
\_geom\_hbond\_distance\_HA  
\_geom\_hbond\_distance\_DA  
\_geom\_hbond\_angle\_DHA

```
_geom_hbond_site_symmetry_A
_geom_hbond_publ_flag
#
#D H A D - H H...A D...A D - H...A symm(A)
#
C7 H7' N3 .98(3) 2.58(3) 3.183(3) 120(2) . yes
C13 H13 O3 .94(4) 2.60(3) 3.465(8) 154(3) . yes
C22 H22 O2 .81(3) 2.55(4) 2.839(4) 103(3) . yes
C23 H23 O42 .81(5) 2.55(5) 3.173(14) 135(5) . yes

# End of Crystallographic Information File
```